



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

NYLOFIX-PT

Product Information

Nylofix-PT is a phenol free, bisphenol free dyefixing agent for polyamide and their blends dyed/printed with acid and metal complex dyestuffs. Polyamide fabric dyefixed with Nylofix-PT shows improvement in wash fastness properties. Nylofix-PT is stable under acidic condition and can be used for various application.

Key Features & Benefits

Key Features

Free from Phenol and Bisphenols

Improves wash fastness properties

Has no effect on shade of dyeings

Benefits

Complies with stringent regulations

Prevents cross-staining during washing

Suitable for any shades

General Characteristics

Physical appearance : Creamish to brown crystalline Powder

Ionic Nature : Anionic

pH of 1% solution : 4 +/- 1

Miscibility : Soluble in water

Compatibility : Compatible with anionic and nonionic products

Stability : Stable to dilute acids and dilute alkalies



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmtkg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

NYLOFIX-PT

Application

I. Exhaust application to improve wet fastness of Polyamide

Nylofix-PT : 2 - 4% (depending on depth of shade)

Bath pH : 4 -4.5

Bath Temp. : 70-80 deg. C

Time : 15-20 min.

Note: For Polyamide / Elastane blend fabric, 4-6% Nylofix-PT is recommended.

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. lose lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]

[Prod.Code :L011852 | Last Upd. On : 17/01/2025] [PP]