



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### AUTOFIN-DR

#### Product Information

Autofin-DR is a finishing agent in liquid form. Autofin-DR has very good adhesive property with various kind of materials. Autofin-DR imparts bulkiness or body to polyester automotive textiles. It is durable to boiling water. Autofin-DR can also be applied on P/V fabric as a potential replacement to body imparting agent.

#### Key Features & Benefits

##### Key Features

Durable finish

Bulkiness and body

Versatile

Used in Automotive industry

##### Benefits

- Durable to Boiling water  
- Withstands multiple home launderings

Potential replacement to body imparting agent

Filling and stiffening agent for interlining fabric, shoe lining fabric and for lining fabric used in leather industry

Abrasion resistance

#### General Characteristics

Physical appearance : Colourless to pale yellow transparent to hazy liquid

Ionic nature : Anionic

pH of 1% solution : 8 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with anionic and nonionic products

Stability : Stable to dilute acids and dilute alkalies

#### Application

Padding process:

Dosage : 60-100 g/l



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### AUTOFIN-DR

Pick-up : 65-70 %  
Bath pH : 5.0-6.0  
Drying : 130-150 deg.C, 90-180 sec.  
Curing : 170-180 deg.C, 30-120 sec. (optional)

Autofin-DR can also be applied by coating technique.

Note:

-----

For interlining fabrics, higher concentration of Autofin-DR is recommended.

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code : L002959.docx | Last Upd. On : 20/01/20 ] [PP]

This is a computer generated report. Hence