

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URLwww.sarex.com

PRODUCT LITERATURE

CAREWHITE-BBU 250%.

Product Information

Carewhite-BBU 250%.is a high affinity fluorescent whitening agent with bluish white shade for cellulosic fibres and their blends. It is suitable for continuous processes as there is no tailing. Carewhite-BBU 250%.is not suitable with cross-linking agent.

Key Features & Benefits

Key Features	Benefits
High affinity	Applicable by exhaust as well as pad application
pH Stability	Stable to pH 6-9

General Characteristics

Physical appearance	:	Greenish yellow powder
Ionic nature	:	Anionic
pH of 1% solution	:	9 +/- 1
Miscibility	:	Miscible with water
Compatibility	:	Compatible with anionic and non-ionic products
Stability	:	Stable to dilute acids and dilute alkalies

Application

```
Exhaust process:
------
1. Optical whitening in aqueous liquor/after bleaching
Dosage : 0.05-0.15%
Time ; 20-30 min
Temp. : 50-80 deg.C
2. Optical whitening in peroxide liquor
Dosage : 0.05-0.15%
Time ; 45-90 min
Temp. : 85-95 deg.C
Padding process:
------
```



501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URLwww.sarex.com

PRODUCT LITERATURE

CAREWHITE-BBU 250%.

Dosage : 0.2-2.0g/1 Pick-up : 65-70 % Bath pH : 6.0-6.5 Drying : 130-160 deg.C, 1-2 mins. STABILITY & FASTNESS PROPERTIES: _____ Stability to Remarks _____ Chlorite bleach Unstable Chlorine bleach Unstable Hard water Stable рΗ 5.5-12 ------Methods Change in degree Fastness properties of whiteness _____ Light fastnessISO 105-B02Wash fastness, 60 deg.CISO 105-C06 C1Wash fastness, 90 deg.CISO 105-C06 E1 3-4 4-5 4 Dry heat fixation, 180 deg.C ISO 105-P01 5 Perspiration, acidic ISO 105-E04 Perspiration, alkaline ISO 105-E04 5 5 Dry Cleaning ____ 5 Chlorine bleach ____ 4 Chlorite bleach 1 ____ _____

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty] [Prod.Code L003568 | Last Upd. On : 10/06/20] [PP]

This is a computer generated report. Hence not signed.