



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email [tcmktg@sarex.com](mailto:tcmktg@sarex.com) URL [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### FABSOFT-LC

#### Product Information

Fabsoft-LC is an economical new generation polysiloxane softener in free flowing pourable form which can be easily diluted to the desired concentration. Fabsoft-LC imparts excellent body break to the finished goods. Fabsoft-LC can be used for cotton, polyester, wool and their blends by pad application. Fabsoft-LC can also be used on garments by exhaust application.

#### Key Features & Benefits

##### Key Features

Economical micro emulsion

Versatile

No adverse effect

##### Benefits

Cost effective finishing recipes

Finishing of garments by exhaust application

Does not impair dry/wet rubbing fastness

#### General Characteristics

Physical appearance : Colourless to straw white liquid  
Ionic nature : Nonionic  
pH of 1% solution : 5 +/- 1  
Miscibility : Miscible with water  
Compatibility : Compatible with cationic, anionic and nonionic products  
Stability : Stable to dilute acids and dilute alkalies

#### Application

##### Padding process

Dosage : 5-15 g/l  
Pick-up : 65-70%  
Bath pH : 5.0-6.0  
Drying : 130-160 deg.C

##### Exhaust process

Dosage : 0.5-1.5%  
Bath pH : 5.0-6.0  
Bath Texp. : 30-40 deg.C  
Time : 20-30 mins.



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### FABSOFT-LC

Note :

-----

pH of bath should not exceed 6.5 (pH of bath should be acidic)

#### Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight.Storage temperature should not exceed 35 deg C.Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]

[ Prod.Code :PF035 | Last Upd. On : 12/06/19 ] [PP]

This is a computer generated report. Hence not signed.