



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARALINK-FF

Product Information

Saralink-FF is a formaldehyde-free cross-linking agent for easy care finish to cellulosic and its blends. It does not affect handle of the fabric. Very good DP rating due to balance of wet and dry crease recovery angle. Strength loss is lower than conventional resin. It also has excellent antipilling properties and good abrasion resistance. It can be applied at wide temperature range. It is also suitable for low temperature curing application.

Key Features & Benefits

Key Features

Formaldehyde-free crosslinking agent

Very good stability to chlorine

Good DP rating and durable to washing and dry cleaning

Benefits

Meets Oekotex Standard 100 requirement

Presence of Chlorine in water does not affect DP rating

Good wet and dry crease recovery angle

General Characteristics

Physical appearance : Yellow Clear liquid

Ionic nature : Non-ionic

pH of 1% solution : 5 +/- 1

Miscibility : Miscible with water

Compatibility : Compatible with cationic, anionic and non-ionic products

Stability : Stable to dilute acids & dilute alkalies

Application

1. Finishing of 100% cotton shirting:

75-150 g/l Saralink-FF

5-10 g/l Sarasoft-MRM (Conc)

15-30 g/l Supernol-PE

15-30 g/l MgCl₂

0.5-1 g/l Sarawet-NF

pad with 60-70% pick-up, curing conditions are mentioned below



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARALINK-FF

2. Garment Dip Process:

6-8% Saralink-FF
2-4% MgCl₂
0.5-0.7% Sarawet-NF
2-3% Supernol-PE
2-4% Sarasoft-MRM (Conc)

M:L=1:10 treat for 20 minutes at 30-40 deg.C
Spin drying - 60% residual humidity
Tumble drying-approximately 10% residual humidity
Steaming-pressing-curing : cure for 10-15 minutes at 155 deg.C (depending on the fabric quality)

* CURING CONDITIONS:
4 minutes at 130-140 deg.C
2 minutes at 150 deg.C
1-2 minutes at 160 deg.C
30 seconds at 170 deg.C

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L011043 | Last Upd. On : 18/11/2022] [PVR]

This is a computer generated report. Hence not signed.