



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

## PRODUCT LITERATURE

### FABCOAT-PU 50 (TF)

#### Product Information

Fabcoat-PU 50 (TF) is a Polyurethane base coating, recommended as a coating compound for outdoor fabrics like cordura. It forms a clear films. To obtain high water column, two coating of Fabcoat-PU 50 (TF) is recommended.

#### Key Features & Benefits

Key Features	Benefits
Easy to coat	Forms clear and tack free films
High water Column	Efficient water proofing
High solid	Higher add on can be achieved

#### General Characteristics

Physical appearance	: White pourable paste with bluish tint
Ionic nature	: Anionic
pH of 1% solution	: 8 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute alkalies and dilute acids

#### Application

Suggested Recipe:

Fabcoat-PU 50 (TF)	: 50-70 Parts
Water	: 45-25 Parts
Saraprint-AC	: 3-5 Parts
Thickener	: To adjust desired viscosity

- Pre-impregnation with flourocarbon is recommended before coating
- Fabcoat-PU 50 (TF) can be applied by knife on air
- Curing should be done at 160 deg.C for 3 mins



# Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email [tcmtg@sarex.com](mailto:tcmtg@sarex.com) URL [www.sarex.com](http://www.sarex.com)

## PRODUCT LITERATURE

### FABCOAT-PU 50 (TF)

- For achieving high add-on, Fabcoat-PU 50 (TF) should be coated in 2 pass
- In case of high water repellency requirement, the fabric must be post impregnated with flourine containing water repellent

#### Precautions

- Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.
- Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]  
[ Prod.Code :L010903 | Last Upd. On : 06/09/22 ] [PVR]

This is a computer generated report. Hence not signed.