



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tomktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

POLYSOFT-55.

Product Information

Polysoft-55. is a new generation silicone softener and works very well on all substrates. It imparts very good surface smoothness and body break on the treated substrates. Another advantage is that it can reduce the caustic during weight reduction process of polyester. It can be applied by padding as well as by exhaust method. Being shear stable, Polysoft-55. can also be used in jet dyeing machine.

Key Features & Benefits

Key features

More Robust than conventional silicone

Excellent Slickness

New silicone back bone

No thermomigration

Benefits

Excellent softness with very good body breakage

Imparts both inner softness and surface smoothness

Incomparable touch

Less migro silicone than conventional silicone

General Characteristics

Physical appearance : Pale yellow hazy liquid
Ionic nature : Nonionic to Weakly Cationic
pH of 1% solution : 4 +/- 1
Miscibility : Miscible with water
Compatibility : Compatible with cationic and nonionic products
Stability : Stable to dilute acids and dilute alkalies

Application

Padding process

Dosage : 10-30 g/l
Pick-up : 65-70%

Exhaust process*

Dosage : 1-3%
Bath pH : 5.0-6.0



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane), Andheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email tcmtkg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

POLYSOFT-55.

Bath pH : 5.0-6.0 Bath Temp : 40-50 deg.C
Drying : 130-160 deg.C Time : 20-30 mins.

* Recommended to use post dyeing at 40-50 deg.C for 20-30 mins.

Note:

pH of bath should not exceed 6.5 (pH of bath should be acidic)

Precautions

Storage : Store in cool, ventilated shed away from heat and direct sunlight. Storage temperature should not exceed 35 deg C. Close lids firmly to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code : L010702.docx | Last Upd. On : 27/10/21] [PVR]

This is a computer generated report. Hence not signed.