



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane),
Anheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email :tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASTABIL-MRS

Product Information

Sarastabil-MRS is an economical organic peroxide stabiliser for exhaust as well as continuous application of hydrogen peroxide bleaching of cotton and cellulosic blends. Apart from good peroxide stabilising action Sarastabil-MRS also chelates certain extent iron present either in the fibre or in the water. Sarastabil-MRS is also suitable for high temperature bleaching and high temperature combined scouring and bleaching of cotton & cellulosic blends.

Key Features & Benefits

Key Features	Benefits
Organic stabiliser	No silicate deposits on fabrics or machines, hence, softer feel
Preferential chelating action on calcium&iron	Catalytic damage to cotton is prevented
Stable to high temp.& alkaline conditions	Combined scouring and bleaching can be carried at 110 deg.C.

General Characteristics

Physical Appearance	: Dark brown liquid
Ionic Nature	: Anionic
pH of 1% solution	: 4 +/- 1
Miscibility	: Miscible with water
Compatibility	: Compatible with anionic and nonionic products
Stability	: Stable to dilute acids and dilute alkalies

Application

1. For combined scouring and bleaching of cotton yarn, hosiery and terry towels, desized fabric for dyeing (MLR 1:3 - 1:12)

2-3%	Caustic soda flakes
1%	Soda Ash
2-3%	Hydrogen Peroxide (50%)



Sarex Chemicals

(A Divn. Of Saraf Chemicals Pvt. Ltd.)

501 Waterford, C Wing, C.D.Barfiwala Marg(Juhu Lane),
Ancheri(W),Mumbai 400 058. INDIA

Phone +91 22 42184218 Fax +91 22 42184350

Email :tcmktg@sarex.com URL www.sarex.com

PRODUCT LITERATURE

SARASTABIL-MRS

0.2-0.3% Sarastabil-MRS
0.5-7% Saradet-NEW OR Celldet-R (0.4 - 0.7%)
0.5 Saralan-JET LF
Treat at 98 deg.C for 45-60 min. or 110 deg.C for 15 min.

2. Combined scouring and bleaching of cotton yarn, hosiery
terry towel, desized fabric for full whites (MLR 1:3-1:12)
- 2-3% Caustic Soda flakes
1 Soda ash
0.5-7% Saradet-NEW OR Celldet-R (0.4 - 0.7%)
0.5 Saralan-JET LF
5-8% Hydrogen Peroxide 50%
0.5-1% Saraquest-2UD
0.5-1.5% Sarastabil-MRS
Treat at 98 deg.C for 90 min. or 110 deg.C for 45 min.

Precautions

Storage : Store in cool, ventilated shed away from
heat and direct sunlight. Storage temperature
should not exceed 35 deg C. Close lids firmly
to avoid contact with air and moisture.

Shelf Life : 9 months from the date of manufacturing, if
stored under controlled conditions.

[The above information is given in good faith and is without warranty]
[Prod.Code :L007002 | Last Upd. On : 08/06/202014] [MOLL]

This is a computer generated report. Hence not signed.